GSTIN: 08AABCS9864Q1ZC



## S.R.S SYNTEX LIMITED

Regd. Office: 40- 41 Om Textile Tower, Pur Road Bhilwara 311001

Email: Info@srsduratech.com

Phone No.: 9166691899, 01482 243098

## **PVC COATED FABRIC**

## SRS 900 GSM BSC

## **UV RESISTANT**

FINISH: TURBO MATT / GLOSS/ LACQUER

TYPE OF YARN: HIGH TENACITY LOW SHRINKAGE POLYSTER YARN

WEAVE: PLAIN
DENIER: 1000D

FIRE RETARDANCY: NFR

PROPERTIES		UNIT	TEST METHOD	SPECIFICATION
Weight		GSM	IS 7016 PART I	900
Thickness		ММ	IS 7016 PART I	0.70
Tensile Strength	Warp Weft	КG/5СМ КG/5СМ	IS 7016 PART II IS 7016 PART II	250 230
Tear Strength	Warp Weft	KG KG	IS 7016 PART III IS 7016 PART III	35 30
Adhesion Strength		кG/5СМ	IS 7016 PART V	8
Water Proofness		ML	IS 7016 PART VII	No leak

AVAILABLE UP TO 3.2M SEAMLESS / STANDARD 50M ROLL LENGTH

The specification and information mentioned are for information purposes and in no way contractually binding. This information is subjected to revision as additional technology is developed. SRS Duratech reserves the right to change/modify the data without prior notice.